



TOGNAZZONI S.R.L.

VIA R. LOMBARDI 18 - 46010 LEVATA DI CURTATONE (MANTOVA)
TEL. 0376/290104 - FAX 0376/290205 - E-MAIL: info@tognazzoni.it

PRODUCT DATA SHEET

GLOVES "GLOVET" top'n soft

Article code	Description
250	GLOVES "GLOVET" TOP'N SOFT
	LENGTH about 85/90 CM. - THICKNESS approx. 27 MY
	Packaging: 50 PIECES BAG
	Country of origin: ITALY
	Non-certified product
	Product composition: ETHYLENE COPOLYMER
	Performed tests and checks: QUALITY CONTROL



TECHNICAL DATA SHEET

FILM USED FOR THE PRODUCTION OF GLOVES 'GLOVET' top'n soft – LENGTH 85/90 CM.
THICKNESS 27 MY approx. - Packaging: No. 50 PIECES (**Art. No. 250**)

TEST	NORM	UNIT OF MEASUREMENT	RESULTS
Breaking load L Breaking load T	ASTM D 882 ASTM D 882	N/mm2 N/mm2	10,6 7,4
Elongation at break L Elongation at break T	ASTM D 882 ASTM D 882	% %	210 638
Tear resistance L Tear resistance T	ASTM D 1004 ASTM D 1004	N N	2,0 1,9
Dynamic COF	ASTM D 1894	Coeff.	0,10
Initial welding temperature	GIFLEX Specifications		Optimum tightness from 90/95 °C

SAFETY DATA SHEET

FILM USED FOR THE PRODUCTION OF GLOVES 'GLOVET' top'n soft – LENGTH 85/90 CM.
THICKNESS 27 MY approx. - Packaging: No. 50 PIECES (**Art. No. 250**)

1)	POLYMERS IDENTIFICATION	Copolymers of ethylene, with the presence of antioxidant, anti-blocking and slip additives.
2)	TOXICOLOGICAL DATA	The products are not classified as hazardous (EEC); all chemicals included are on the ACOIN, EINECS, TSCA lists.
3)	FLAMMABILITY	The products burn, but are not classified as flammable; 'Flash Point' approx. 360 degrees C.
4)	FIRE EXTINGUISHING MEDIA	The following media can be used: water spray, dry powder, foam, carbon dioxide.
5)	USE	Volatile hydrocarbon substances may be formed during processing and during heat treatment of the film; these should not be inhaled but ventilated externally.
6)	ENVIRONMENT	The products are not considered environmentally hazardous.
7)	DISPOSAL	The materials making up the film are, subject to compliance with current legislation, to be considered inert waste, to be disposed of in a controlled landfill or by incineration; proper combustion does not require special flue gas control technologies.
8)	RECYCLING	The film is fully recyclable and is routinely recycled with polyethylene waste.

The information and data contained herein are provided by us with the best of accuracy. However, this accuracy is not the subject of a guarantee and the data provided do not constitute or imply, in general terms, any guarantee or commitment by the Company. Any rights of patent holders are expressly reserved.