

TOGNAZZONI S.N.C. DI ANDREA E ALESSANDRO TOGNAZZONI

VIA R. LOMBARDI 18 - 46010 LEVATA DI CURTATONE (MANTOVA)
TEL. 0376/290104 - FAX 0376/290205 - E-MAIL: info@tognazzoni.it

PRODUCT DATA SHEET

ZOOTECHNICAL ELASTIC GLOVES

Article code	Description
200	ZOOTECHNICAL ELASTIC GLOVES LENGTH CM. approx. 85 - THICKNESS 27 MY
	Packaging: 50 PIECES BAGS
	Country of origin: ITALY
	Non-certified product
	Product composition: ETHYLENE COPOLYMER
	Performed tests and checks: QUALITY CONTROL



DATA SHEET

FILM USED FOR THE PRODUCTION OF ZOOTECHNICAL ELASTIC GLOVES
LENGTH about CM. 85 - THICKNESS 27 MY approx. - Packaging: N. 50 PIECES (**Art. code 200**)

TEST	NORM	UNIT OF MEASUREMENT	RESULTS
Thickness	ASTM D 882	MY	27
Car. Rott. L Car. Rott. T	ASTM D 882 ASTM D 882	N/mm2 N/mm2	15,7 17
Mod. 100 % L Mod. 100 % T	ASTM D 882 ASTM D 882	N/mm2 N/mm2	10,1 6,08
Mod. 300 % L Mod. 300 % T	ASTM D 882 ASTM D 882	N/mm2 N/mm2	14,9 8,98
All. Rott. L All. Rott. T	ASTM D 882 ASTM D 882	% %	345 567
Res. Lace. L Res. Lace. T	ASTM D 1004 ASTM D 1004	N N	1,77 1,66
COF Stat. COF Din.	ASTM D 1894 ASTM D 1894	Coeff. Coeff.	0,182 0,167
Weldability	Hot-Tack	T'C min.	80

The information and data contained herein are provided by us with the best of accuracy. However, this accuracy is not the subject of a guarantee and the data provided does not constitute or imply, in general terms, any guarantee or commitment by the Company. Any rights of patent holders are expressly reserved.

SAFETY DATA SHEET

FILM USED FOR THE PRODUCTION OF ZOOTECHNICAL ELASTIC GLOVES
 LENGTH about CM. 85 - THICKNESS 27 MY approx. - Packaging: N. 50 PIECES (**Art. code 200**)

1)	CHEMICAL NATURE OF THE PRODUCT	Substance Ethylene copolymer, presence of anti-oxidant, slip agents and anti-blocking additives
2)	PHYSICAL PROPERTIES <ul style="list-style-type: none"> • PHYSICAL STATUS..... • CHARACTERISTIC TEMPERATURES..... • SOLUBILITY • DENSITY 	At 20° C: plastic film Colour: translucent Smell: estery At melting: 70 to 105° C. From the start of decomposition: approx. 350° C. In water at 20° C.: not soluble From 0.92 to 0.98 g/cm3
3)	TOXICOLOGICAL INFORMATION	These polymers can be regarded as: - non-irritating to skin and eyes - practically not harmful if swallowed Thermal decomposition products may be irritating to skin and mucous membranes.
4)	FIRST AID MEASURES	<ul style="list-style-type: none"> - In case of contact with hot product: treat as a thermal burn without chemical action (wash immediately and thoroughly with cold water). - Inhalation of thermal decomposition products: go to fresh air, consult a doctor.
5)	ENVIRONMENTAL PROTECTION	Do not dispose of into drains or the natural environment. Comply with current prefectural regulations and decrees.
6)	SPECIAL INDICATIONS	This document applies to the product IN ACCORDANCE with the specifications provided by the TOGNAZZONI S.N.C. suppliers. The information contained in this technical data sheet is given in good faith and based on our latest knowledge of the product at the date of issue. The user's attention is drawn to the possible risks involved when a product is used for purposes other than those for which it is intended. This sheet must not be used or reproduced except for the purposes of prevention and safety.