

TOGNAZZONI S.N.C. DI ANDREA E ALESSANDRO TOGNAZZONI

VIA R. LOMBARDI 18 - 46010 LEVATA DI CURTATONE (MANTOVA)
TEL. 0376/290104 - FAX 0376/290205 - E-MAIL: info@tognazzoni.it

PRODUCT DATA SHEET

APRONS MADE OF POLYURETHANE

Item

Description

906

APRONS MADE OF NEUTRAL POLYURETHANE
MEASURE CM. 95 x 130 – THICKNESS 250 MYN.

Packaging: BAG OF N. 1 PIECE

Country of origin: ITALY

Not certified product

Composition of the product: POLYETHER POLYURETHANE

Tests and checks carried out: QUALITY CHECK



DATA SHEET

FABRIC USED FOR THE PRODUCTION OF NEUTRAL POLYURETHANE APRONS - SIZE CM. 95 x 130
THICKNESS 250 MYN. 1 PIECE (**Item 906**)

Composition		POLYETHER POLYURETHANE	
Mechanical-physical characteristics			
<i>Nominal thickness</i>	250	$\mu \pm 10\%$	
<i>Colour</i>	Unpigmented		
<i>Appearance</i>	Standard		
<i>Hardness</i>	86	Sh.A ± 5	ASTM D2240
<i>Modulus at 100% strenght</i>	6	N/mm ² $\pm 10\%$	ISO 37
<i>Modulus at 300% strenght</i>	10	N/mm ² $\pm 10\%$	ISO 37
<i>Max. production width</i>	1500	mm ± 5	
<i>Load at break</i>	35	N/mm ² $\pm 10\%$	ISO 37
<i>Elongation at break</i>	550	% $\pm 30\%$	ISO 37
<i>Tear strenght</i>	70	N $\pm 30\%$	ISO 6383/1
<i>Melting point</i>	160	°C ± 10	ASTM D3417
<i>Softening point</i>	80	°C	DIN 53460
<i>Store keeping temperature</i>	-20 +40	°C	
<i>Abrasion resistance</i>	100	mm ³ ± 20	DIN 53516
<i>UV resistance</i>	3		ISO 4892-3
<i>Skin approved</i>	Yes		USP class VI
<i>FDA approved</i>	Yes		Food and Drugs Adm.
<i>RoHS approved</i>	Yes		2002/95/CE RoHS
Note			
<i>Product free of Formaldehyde, Latex, PVC, TBT, MBT, DBT</i>			

The data represent the average values tested in our laboratory at normal environment conditions. This information is given without guarantee. It is expressly understood and agreed that the Customer assumes, and hereby releases TOGNAZZONI from, all liability: in tort, contract or otherwise, incurred in connection, with the use of our products, technical assistance and information. Data are subject to alteration without notice.